

Product Data Sheet

No. 1180 - 01/17

EAGLE SPRAY PAINT - AEROSOL

CARB VOC/MIR: Flat <60%/0.80; Non-Flat <65%/0.95; Metallic <80%/1.25

PRODUCT NUMBERS:

S180 - ALUMINUM	S186 - FLAT BLACK	S192 - GLOSS WHITE	S202 - SHERWOOD GREEN
S182 - CHOCOLATE BROWN	S188 - FLAT WHITE	S193 - SEMI-GLOSS WHITE	S205 - GRAY
S184 - FIRE RED	S190 - GLOSS BLACK	S196 - LEMON YELLOW	S206 - CLEAR
S185 - ORANGE	S191 - SEMI-GLOSS BLACK	S198 - MALIBU BLUE	S220 - ALMOND

I. GENERAL DESCRIPTION

Description: This all purpose enamel coating is formulated for interior and exterior use on a variety of surfaces. A superior quality, tough, durable finish that prevents rust and dries in minutes.

Benefits: Eagle Spray Paint provides excellent adhesion to all metal, wood and masonry surfaces. Good gloss and hide coverage. Protects metal and wood from rust and corrosion. Dry to touch in 15 minutes. Get a smooth, professional finish every time.

Application: Great for furniture, metal and wood railings, fences, bicycles, hobbies, crafts, plastic and metal garden accessories, cabinets, doors, patio items, wicker, tools and masonry, bulkheads, and much more. Can be used indoors or outdoors.

Directions: Align spray head with red mark on valve rim to ensure complete evacuation. Before spraying, shake can vigorously for at least one minute after rattle of agitator ball is heard. Surfaces must be dry and free of dust, dirt, oil, grease, wax and other contaminants that would adversely affect paint adhesion. On bare metal or lightly rusted surfaces, Zynolyte Multi-Purpose Primer is recommended prior to finish color application. Extremely slick, glossy surfaces should be lightly sanded. Wipe surface with tack cloth to remove debris. Use only when can temperature is between 60° F and 80° F (16° C and 27° C). Mask and protect areas not to be sprayed to reduce clean up. Hold can 10 to 12 inches from surface to be coated, and press spray head firmly. Use steady, even strokes while spraying. Two light coats are better than one heavy coat. Wait one to two minutes before recoat. Spray in well ventilated area. To prepare can for storage, turn can upside down and press spray tip for 2 seconds to clear paint from valve and tip.

Limitations: Please refer to the Safety Data Sheet for specific information on material hazards, etc.

Packaging:

Cans (20 oz.)	10 oz. net wt. (284 g)	13.4 fl. oz. (396 ml)
Case 12 cans/case	12 lbs. (5.4 kg)	0.47 CF (0.013 CM)

II. CHARACTERISTICS & PROPERTIES (Average for all colors)

Specifications: Complies with CARB VOC & MIR regulations

Appearance:

Gloss at 60° F Flat <5/ Semi-Gloss 35-60/Gloss 90
Class Flat, Semi-Gloss, Gloss, Metallic

Coverage:

Theoretical-at 1 mil dry 13 sq. ft./can
Practical-at 1/2 mil dry 26 sq. ft./can

Dry Schedule: (At 77° F [25° C], 50% Humidity at 1 mil dry)

To touch 15 min.
To handle 30 min.
To recoat Before 2 hrs. or after 72 hrs.
Full cure 72 hrs.

Performance and Chemical Properties:

Weight per gallon 5.86 lbs.
Specific gravity 0.702
Viscosity Not Applicable
Flammability: Label marking Extremely Flammable
Flash point <0°F (-18°C)
Operating temperature range 50°F to 90°F (10° to 32°C)
Percent solids by weight 14%
Percent solids by volume 8%
Percent pigment by volume 1%
VOC Level (Flat, Non-flat, Metallic)..... <60%; <65%; <80%
CARB MIR (Flat, Non-flat, Metallic) <0.8; <0.95; <1.25
Dielectric strength N/A
Interior durability Excellent
Exterior durability Excellent
Temperature resistance 200° F (93° C)
Color fastness Excellent
Adhesion Excellent over properly prepared surfaces
Mineral Spirits resistance Good
Gasoline resistance Poor
Motor oil resistance Good
Pencil hardness (ASTM D3363)..... H
Salt spray corrosion (ASTM B117) 200 hrs.

Base Materials:

Resin system Acrylic VT Alkyd
Solvents Acetone, VM&P Naphtha
Propellent: Hydrocarbon

III. SHIPPING, STORAGE AND HEALTH

UN number UN1950
Proper Shipping Description Aerosols
Hazard Class 2.1
Packing Group N/A
Limited Quantity Yes
Warehouse storage level number NFPA 30B Level 2
Storage temperature 32° to 120°F (0° to 49°C)
Shelf life 1 to 2 years

HMIS ratings

Health 1
Fire 3
Reactivity 1

IV. MISCELLANEOUS

Contains no Ozone Depleting Substances (O.D.S.)

V. WARRANTY

1-year warranty to the original registered owner on all products from date of purchase. User returns, exchanges and defective refunds must be made with the original place of purchase. Because Aervoe cannot control Buyer's handling or use of product, Aervoe makes no warranty expressed or implied when not used or stored in accordance with directions. Aervoe shall not be liable for cost of labor, incidental or consequential damages, and this warranty is limited to replacement or repair of product or credit of purchase.